

TECHNICAL DATA SHEET

DIMENSIONS

FORMAT

| | |
|---------------------------|--------------|
| Length | 1261 mm |
| Width | 192 mm |
| Number of panels per pack | 9 |
| m ² per pack | 2.179 |
| Bevels | 4V lacquered |
| Thickness | 8 mm |
| Tongue and groove | Uniclic |
| Water resistant | No |

FACTORY WARRANTY

| | METHOD | PARAMETERS | VALUES | |
|-------------|-------------------------|-------------------------|-----------------------|----------------|
| Usage class | EN 13329 | | Class | 21-22-23/31-32 |
| CE | EN 14041:2004 / AC:2006 | Notified body | NB 0766 - EPH Dresden | DOP : On pack |
| UKCA | EN 14041:2004 / AC:2006 | Approved body | AB 0321 - Satra UK | DOP : On pack |
| | Residential use | See warranty conditions | | |
| Warranty | Commercial use | See warranty conditions | | |
| | Water resistancy | See warranty conditions | | |

GENERAL DATA (ACCORDING TO EN 13329)

| | METHOD | PARAMETERS | NORM REQUIREMENTS | VALUES |
|---------------------------|---|-----------------------------|--|--------------------|
| Wear resistance | EN 13329 | | ≥ 4000 cycles | ≥ 6000 cycles |
| Wear class | EN 13329 | | AC4 | AC5 |
| Impact resistance | EN 17368d | Small ball | ≥ 35mm | ≥ 35mm |
| | EN 13329 | Big ball | ≥ 750mm | ≥ 750mm |
| Scratch resistance | EN 438-2, 25 | | Charge ≥ 3N | Charge ≥ 3N |
| Effect of a castor chair | ISO 4918 (with underlay) | Type W (EN 12529) | 25000 cycles | No change |
| Thickness swelling | ISO 24336 | After 24h immersion at 20°C | ≤ 18% | ≤ 18% |
| Locking strength | ISO 24334 | F10,2 long side | ≥ 1 kN/m | ≥ 1 kN/m |
| | | Fmax long side | | ≥ 1 kN/m |
| | | Fs0,2 short side | ≥ 2 kN/m | ≥ 2 kN/m |
| | | Fmax short side | | ≥ 2 kN/m |
| Effect of a furniture leg | EN 424 | | No damage shall be visible, when tested with foot type 0 | No visible damage |
| Resistance to staining | EN 438 | Group 1,2 Group 3 | Class 5 Class 4 | Class 5 Class 4 |
| Light fastness | EN ISO 4892 2:2006/A1:2009 Procedure B - Cycle 5 | Grey reference | Class ≥ 4 | Class 4 |

ENVIRONMENT, SAFETY & HEALTH

| | METHOD | PARAMETERS | NORM REQUIREMENTS | VALUES |
|-----------------------|---------------|--------------------|-------------------|--------------------------|
| Formaldehyde emission | EN 717-1 | ppm | E1 < 0,1 | < 0,01 |
| Anti-static | EN 1815 | | ≤ 2,0 kV | ≤ 2,0 kV |
| Reaction to fire | EN 13501-1 | Class | | Cfl-s1 |
| Thermal resistance | EN 12996:2001 | m ² K/W | | 0,055 m ² K/W |
| Slip resistance | EN 13893 | μ | μ ≥ 0,30 | DS: μ ≥ 0,30 |



EN 14041:2004 / AC:2006
Germany Floorcoverings
EN 13329:2016

EN 14041:2004 / AC:2006
Germany Floorcoverings
EN 13329:2016